



# LEHIGH VALLEY PLASTICS

We Shape The Industry

TYPICAL PROPERTIES OF TEFLON		
PROPERTY	ASTM Method	
Tensile Strength, 73 degrees	D638-52T	1,500 - 3,000 lb./sq.in
Elongation 73 degrees Fahrenheit	D638-52T	100-200%
Hardness, Durometer	D676-49T	D50-D60
Coefficient of linear thermal expansion per 73 - 100 degrees Fahrenheit	D696-44	5.5 X 10 to the -5 power
Thermal conductivity, 0.18 in	Cenco-Fitch	1.7 B.T.U./hr./sq. ft./ degrees Fahrenheit /in.
Heat-distortion temperature 66 lb./sq.in.	D6488-45T	250 degrees Fahrenheit
Dielectric strength, short time, 0.080 in.	D149-44	400-500 v/mil
Dielectric constant, 60 cycles - greater than 3,000 megacycles	D150-54T	2.1
Dissipation factor, 60 cycles - greater than 3,000	D150-54T	less than 0.0003
Water-absortion	D570-42	less than 0.01%
Flamability	D635-44	non-flamable
Specific Gravity	D792-50	2.1 - 2.2
Resistance to weathering	-	Unaffected by 25 yrs. exposure in Florida
Static or kinetic coefficient	-	0.04

IMPORTANT: The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. Lehigh Valley Plastics, Inc. will not be held responsible for the use of this information relative to actual application.



**LEHIGH VALLEY  
PLASTICS**

We Shape The Industry

### Teflon® Filled Properties

COMPOSITION	Chemically Modified PTFE with Glass Fiber Filler	Chemically Modified PTFE with Carbon Filler
COLOR	Green	Black
ASTM F-36 COMPRESSIBILITY (%)	10	7
ASTM F-36 RECOVERY (%)	33	33
ASTM F-37 (B) SEALABILITY (ML/MN) (%)	0.02	0.07
ASTM F-38 (B) CREEP RELAXATION	15	17
ASTM F-152 TENSILE STRENGTH (PSI)	2140	2405
ASTM D-792 (B) SPECIFIC GRAVITY	2.24	2.11

\* Testing performed by independent test laboratory.

\*\* Color will vary depending on wall thickness.

IMPORTANT: The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. Lehigh Valley Plastics, Inc. will not be held responsible for the use of this information relative to actual application.