



## PVC Typical Properties

Property	Units	Value	ASTM Method
<b>Physical</b>			
Density	g/cm <sup>3</sup>	1.42	D 792
Water Absorption	%	0.06	D 570
Rockwell Hardness	R Scale	115	D 785
Shore Durometer	D	89	D 2240
Cell Class	—	12454-B	1784
<b>Mechanical</b>			
Tensile Modulus	psi	411,000	D 638
Yield Strength	psi	7,500	D 638
Flexural Modulus	psi	481,000	D 790
Yield Strength	psi	12,800	D 790
Izod Impact	ft-lb/in	1.0	D 256
<b>Thermal</b>			
Vicat Softening Point	°C/°F	83/181	D 1525
Heat Deflection Temperature	°C/°F	82/179	D 648
Heat Deflection Temperature	°C/°F	80/176	D 648
Linear Coefficient of Expansion	in/in/°C	$5.8 \times 10^{-5}$	D 696
Linear Coefficient of Expansion	in/in/°F	$3.2 \times 10^{-5}$	D 696
<b>Flammability Rating</b>			
Flammability	—	Self-Extinguishing	D 635
Flammability	—	0	UL 94V
Flame Spread	—	15	E 84
<b>Chemical</b>			
Chemical Resistance	—	Class B	D 1784
<b>Electrical</b>			
Electrical Volume Resistivity	Ohm/cm	$5.4 \times 10^{15}$	D 257
Dielectric Constant	60 Hz	3.19	D 150
Dissipation Factor	60 Hz	0.0096	D 150
Loss Index	60 Hz	0.030	D 150
Dielectric Strength	Volts/mil	544	D 149

IMPORTANT: The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. Lehigh Valley Plastics, Inc. will not be held responsible for the use of this information relative to actual application.